



BU Anchor

Prüfbescheinigungen
EN 10204
Inspection Documents

HILTI Aktiengesellschaft
Feldkircherstrasse 100
FL-9494 Schaan
Fürstentum Liechtenstein

Dokument /
Document

Nr: 40/26112012

Prüfbescheinigung / Inspection Document

Werkzeugnis	-	Test report	2.2	<input checked="" type="checkbox"/>
Abnahmeprüfzeugnis	-	Inspection certificate	3.1	<input type="checkbox"/>

Artikel-Nr. Item-# Code art.	Produktbezeichnung Product designation Réfèrence produit	Auftrags-Nr. Order-# Votre commande	Charge / Los-Nr. Batch-code Commande No.	Menge Quantity Quantité
419105	Threaded rod AM20x1000 8.8 HDG			

Bemerkungen:
Remarks:
Remarques:

Hiermit bestätigen wir, dass die oben angeführte Lieferung den Vereinbarungen bei der Bestellung entspricht.
We herewith certify, that the material described above complies with the terms of the order.
Nous certifions que la livraison est conform aux stipulations de la commande.

Issuer:

Name : Aniko Huebner-Borbely
Street : Feldkircherstrasse 100
City : 9494 Schaan
Country : Fürstentum Liechtenstein

Verantwortliche Stelle
Responsible Department
Service responsable

Datum / Date: 26.11.2012





BU Anchor

Prüfbescheinigungen
EN 10204
Inspection Documents

HILTI Aktiengesellschaft
Feldkircherstrasse 100
FL-9494 Schaan
Fürstentum Liechtenstein

CERTIFICATE

2.2

Size : M20X1000

Nr. : 419105

Specification: ISO 898-1(2009) 8.8

Chemical composition

	C (c)	Si	Mn	P	S	Ni	Cr	Mo	Cu	Al	Pb	Sn	B
Min.	0.15 / 0.25												
Max.	0.40 / 0.55			0.025	0.025								
Results	0.50	0.27	0.60	0.014	0.019								

(c) See notes in norm ISO 898-1 table 2

Mechanical properties

	Yield Strength. R _{p0.2} N/mm ² ≤M16-->M16	Tensile Strength. R _m N/mm ² ≤M16-->M16	Elongation A %	Impact strenght K, Joules (charpy)	Hardness Rockwell HRC ≤M16-->M16	Reduction after fracture Z %
Min.	640 - 660	800 - 830	12%	27(-20°C for ≥M16)	22 - 23	52%
Max.					32 - 34	
Results	832	954	14	52	28	53

Remarks :Material harden and tempered on min.425°C

All information given is based on original certificates or own tests on the material in cold drawn, or finished condition.